

STATE OF ISRAEL

-		-1-	Service and the service and th		
REC'D	İ	Î	NOV	1998	7
WIPO		$\overline{}$	CT		
******		-	-		- 7

This is to certify that annexed hereto is a true copy of the documents as originally deposited with the patent application particulars of which are specified on the first page of the annex, זאת לתעודה כי רצופים בזה העתקים נכונים של המטמכים שהופקרו לכתחילה עם הבקשה לפטנט לפי הפרטים הרשומים בעמוד הראשון של הנספת.


PRIORITY DOCUMENT

SUBMITTED OR TRANSMITTED IN COMPLIANCE WITH RULE 17.1(a) OR (b)

This 2 5 -10- 1998

רשם הפטנטים Registrar of Patents

ד"ד מרגוט גנץ
יועצת בכירה לרשם חפטנטים
נתאשר





REQUEST

The undersigned requests that the present international application be processed according to the Patent Cooperation Treaty.

For r	ng Office use only
International Application No.	PCT/IL 97/00391
	(27.11.97)
International Filing Date	27 NOVEMBER 1997
ISRAEL PA	ATENT OFFICE
PCT Interna Name of receiving Office and	tional Application "PCI International Application"

	Applicant's or agent's file reference (if desired) (12 characters maximum)
Box No. I TITLE OF INVENTION COATING SYSTEM FOR SUBSTRATES	(1) desired (12 characters maximum)
Box No. II APPLICANT	
Name and address: (Family name followed by given name; f designation. The address must include post	for a legal entity, full official real code and name of country.) This person is also inventor.
INDIGO N.V. LIMBURGLAAN 5 6221 SH MAASTRICHT NETHERLANDS	Telephone No. +31 43 35 65 656
NETHERLANDS	Facsimile No. +31 43 35 65 600
·	Teleprinter No.
State (i.e. country) of nationality: NETHERLANDS	State (i.e. country) of residence: NETHERLANDS
This person is applicant all designated for the purposes of:	nated States except the United States the States indicated in the States of America only the Supplemental Box
Box No. III FURTHER APPLICANT(S) AND/OR (FU	URTHER) INVENTOR(S)
Name and address: (Family name followed by given name; designation. The address must include pos	stal code and name of country.) This person is:
2 HALUTZ STREET REHOVOT 76251 ISRAEL	applicant only applicant and inventor
	inventor only (If this check-box is marked, do not fill in below.)
State (i.e. country) of nationality: ISRAEL	State (i.e. country) of residence: ISRAEL
This person is applicant all designated all designated for the purposes of:	gnated States except the United States the States indicated in the States of America only the Supplemental Box
Further applicants and/or (further) inventors are indicate	ed on a continuation sheet.
Box No. IV AGENT OR COMMON REPRESENTA	TIVE; OR ADDRESS FOR CORRESPONDENCE
The person identified below is hereby/has been appointed to of the applicant(s) before the competent International Autho	act on behalf rities as: agent common representative
Name and address: (Family name followed by given name designation. The address must include po	r; for a legal entity, full official Telephone No. ostal code and name of country.) +972 3 921 5380
FENSTER, Paul; FENSTER, Maier; WEISS, Phil	Facsimile No.
FENSTER & COMPANY PATENT ATTORNEYS LTD.	+972 3 921 5383 Teleprinter No.
P.O. BOX 2741 49127 PETACH TIKVA, ISRAEL	
Mark this check-box where no agent or common reprindicate a special address to which correspondence sh	esentative is/has been appointed and the space above is used instead to nould be sent.

Sheet	No		2	
JIICCL	110.	٠		١

•	

Continuation of Box No. III FURTHER APPLICANTS	S AND/OR (FURTHER)	INVENTORS
If none of the following sub-boxes is use	d, this sheet is not to be in	cluded in the request.
Name and address: (Family name followed by given name; for designation. The address must include postal c BRANDISS, Sergio YAVETZ 11 REHOVOT 76252 ISRAEL	a legal entity, full official code and name of country.)	This person is: applicant only applicant and inventor inventor only (If this check-box is marked, do not fill in below.)
State (i.e. country) of nationality: ISRAEL	State (i.e. country) of resid	
	1	nited States the States indicated in the Supplemental Box
Name and address:(Family name followed by given name; for designation. The address must include postal a	a legal entity, full official code and name of country.)	This person is: applicant only applicant and inventor inventor only (If this check-box is marked, do not fill in below.)
State (i.e. country) of nationality:	State (i.e. country) of resi	dence:
This person is applicant all designated all designate for the purposes of:		Inited States the States indicated in the Supplemental Box
Name and address: (Family name followed by given name; for designation. The address must include postal	a legal entity, full official code and name of country.)	This person is: applicant only applicant and inventor inventor only (If this check-box is marked, do not fill in below.)
State (i.e. country) of nationality:	State (i.e. country) of res	sidence:
		Jnited States the States indicated in the Supplemental Box
Name and address: (Family name followed by given name; for designation. The address must include postal	r a legal entity, full officia l code and name of country.)	This person is: applicant only applicant and inventor inventor only (If this check-box is marked, do not fill in below.)
State (i.e. country) of nationality:	State (i.e. country) of res	sidence:
This person is applicant all designated all designate for the purposes of:		United States the States indicated in the Supplemental Box
Further applicants and/or (further) inventors are indicated	on another continuation shee	t.

Sheet No.	

Box No	o.V	DESIGNATION OF STATES			
The fo	llowin	ng designations are hereby made under Rule 4.9(a)	(mark	the a	aplicable check haves; at least one must be made the
Region			(11227	. uie cq	opinicable check-boxes; at least one must be marked):
_					·
☒		ARIPO Patent: GH Ghana, KE Kenya, LS Les ZW Zimbabwe, and any other State which is a Contra	ıcting	State	of the Harare Protocol and of the PCT
Ճ	EA	Eurasian Patent: AM Armenia, AZ Azerbaijan, Moldova, RU Russian Federation, TJ Tajikistan, TW of the Eurasian Patent Convention and of the PCT	BY I	Belaru kmeni	s, KG Kyrgyzstan, KZ Kazakstan, MD Republic of stan, and any other State which is a Contracting State
M	EP	European Patent: AT Austria, BE Belgium, CH an ES Spain, FI Finland, FR France, GB United Kingdon NL Netherlands, PT Portugal, SE Sweden, and any Convention and of the PCT	n.GF	l Gree	erland and Liechtenstein, DE Germany, DK Denmark, ce. IE Ireland, FT-Italy, LU-Luxembourg, MC Monaco, which is a Contracting State of the European Patent
Ø	OA	GA Gabon, GN Guinea, ML Mali, MR Mauritania, which is a member State of OAPI and a Contracting S	NE N State	liger, : of the	Republic, CG Congo, CI Côte d'Ivoire, CM Cameroon, SN Senegal, TD Chad, TG Togo, and any other State PCT (if other kind of protection or treatment desired, specify
Natio	nal P	atent (if other kind of protection or treatment desired,			
×		Albania	⊠.		Larvia
Ø		Armenia	Ø		Republic of Moldova
×		Austria	Ø		Madagascar
		Australia	_		
×		Azerbaijan	X	IVALES	The former Yugoslav Republic of Macedonia
×		-	6 2	M	March 1
		Bosnia and Herzegovina	X		Mongolia
- N			Ø		Malawi
		Bulgaria			Mexico
_		Brazil	M		Norway
		Belarus	\boxtimes		New Zealand
		Canada	Ø		Poland
		and LI Switzerland and Liechtenstein	M	PT	Portugal
	CN	China	\boxtimes	RO	
	CU	Cuba	\boxtimes	RU	Russian Federation
	CZ	Czech Republic	\boxtimes	SD	Sudan
	DE	Germany	\boxtimes	SE	Sweden
	DE	Denmark	\boxtimes	SG	Singapore
	EF	Estonia	Ø	SI	Slovenia
🛭	ES	Spain	Ø	SK	Slovakia
	FI	Finland	Ø	SL	Sierra Leone
	G	United Kingdom		TJ	Tajikistan
	GI	Georgia	⊠	TM	Turkmenistan
🗵	G	I Ghana	<u> </u>	_	- .
	H	J Hungary	×	TT	Trinidad and Tobago
	П	Israel	×	UA	
	IS	Iceland	×		
⊠] JF	Japan			United States of America
⊠	K				•••••
⊵	K	G Kyrgyzstan	Z	T UZ	Uzbekistan
⊠			E		Viet Nam
1		*************	B		Yugoslavia
⊵	3 K	R Republic of Korea	8		V Zimbabwe
1 2		Z Kazakstan	<u>_</u>	heck-t	oxes reserved for designating States (for the numoses of
	_	C Saint Lucia	a	nation	al patent) which have become party to the PCT after
[2	3 L	K Sri Lanka	13	11.	DONESIA
1 2		R Liberia	Č		***************************************
1 2		S Lesotho	Č	_	***************************************
1 7		T Lithuania	ב	_	
	_	U Luxembourg	֖֖֝֞֞֜֝֝֟֜֝ ֪	=	
In un	addi der th	ti n to the designati ns made above, the applicant also PCT except the designation(s) of	so ma	ikes ur	der Rule 4.9(b) all designations which would be permitted

The applicant declares that those additional designations are subject to confirmation and that any designation which is not confirmed before the expiration of 15 months from the priority date is t be regarded as withdrawn by the applicant at the expiration of that time limit. (Confirmation of a designation consists of the filing of a notice specifying that designation and the payment of the designation and confirmation fees. Confirmation must reach the receiving Office within the 15-month time limit.)

				4		
Sheet	NI ~			-		
Sueer	INO.	٠	٠	٠	٠	

(No. VI PRIORITY CI			er priority claims a			
priority of the following ea			1		Offic	e of filing
Country which, or for which, the application was filed)	Filing (day/mon		Applica	tion No.	(only for internation	regional or al application)
n (1)	12 Octob	oer 1997	121951			
AEL	(12-1	0-97)	121331			
n (2)				the state of the s		
	(<u> </u>			
m (3)		,				* .
irk the following check-box	f the certified cop	of the earlier ap	plication is to be i	ssued by the	Office which for the	ne purposes of the
scant international applicall	on is the receiving					
The receiving Office is Bureau a certified copy	of the earlier appl	ication(s) identifi	ed above as item(e)): <u>(1)</u>		
	IONAL SEARCH					
noice of International Searce competent to carry out the inte						<u> </u>
e competent to carry out the inte arlier search Fill in where o	search (internation	al, international-ty	pe or other) by the	International	Searching Authori	ty has already been
arlier search Fill in where of it or requested and the Authori ch search or request either by r	ty is now requested	to base the interne	ational search, to the	e extent possi of) or by refer	ble, on the results of ence to the search re	inat eartier search. quest:
ch search or request either by rountry (or regional Office):	ejerence to the relevi	ant application (or /month/year):		Nu	mber:	
Junu's (or regional Office).		, ,				
Box No. VIII CHECK LI	ST				the item(=)	ed below.
This international applica	tion contains	This internation	nal application is ac rate signed	companied to	by the item(s) mark fee calculation sh	
the following number of s	heets:	r. L_l pow	er of attorney	ليا ٠٠		
1. request :	4 sheets 8 sheets	2. Copy	y of general ver of attorney	6.	separate indication	rganisms
2. description : 3. claims :	5 sheets		ement explaining	2 I	nucleotide and/or	amino acid
4. abstract :	1 sheets	lack	of signature	الا "	sequence listing	(diskette)
5. drawings :	0 sheets	4. pric	ority document(s) attified in Box No. 1	7 8. 🔲	other (specify):	
Total :	18 sheets		tem(s):			
Figure No	of the drawings (if	any) should acco	mpany the abstract	when it is p	ublished.	
Per No IV SIGNATIO	RE OF APPLICA	NT OR AGENT				
Next to each signature, indi	cate the name of t	the person signin	g and the capacity	in which th	ne person signs (if	such capacity is n
obvious from reading the rea	quest).				••	
Ω						
Vaul Fenst	zu					
FENSTER, Paul AGENT						
AGENT	_					
		 For receiving 	g Office use only			2. Drawings
Date of actual receipt o international application	n:		EMBER 1997	7)	7.11.97)	received:
Corrected date of actual timely received papers purported international	or drawings comp	eting the				
Date of timely receipt of corrections under PCT	of the required Article 11(2):					not receive
5. International Searching	Authority TO A	VEP	6. Transr	nittal of sear	ch copy delayed	
specified by the applic	ant: ISA	VEP	until s	earch fee is p	paid	

10

15

20

25

30

COATING SYSTEM FOR SUBSTRATES

FIELD OF THE INVENTION

The present invention is related to the field of printing and in particular to a method of coating substrates to improve adhesion of toner images thereto.

BACKGROUND OF THE INVENTION

Problems of transfer and adhesion of toner images and in particular of liquid toner images, to substrates, is well known. Transfer of images may be effected by electrostatic transfer of toner particles to the substrate, either from an imaging surface such as a photoreceptor or from an image transfer member. Alternatively, image transfer may be effected by heat and pressure, generally from an intermediate transfer member to which the image is first transferred from the imaging surface. Image transfer from an intermediate transfer member, on which the image is generally in a molten state, is often problematic. Usually, some treatment of the substrate surface is required in order to enable good transfer and fixing.

Transfer and adhesion of toner is improved by chemical compatibility of the toner and the substrate for example, chemical bonding by acid-base interaction or chemical similarity leading to mutual bonding.

A common solution to transfer and adhesion problems is the coating of a substrate with an adhesion enhancer, which has an affinity for both the toner material and the substrate. For example, the adhesion of the above mentioned toner types to PET and BOPP can be greatly enhanced by coating the substrates with a layer of Macromelt 6239 (Henkel) which is an amine terminated polyamide. This material adheres well to the substrate and has a high affinity for the toner particle polymer as well. However, it has been found that the shelf life of such coated substrates is limited and the quality of the transfer of toner from an intermediate transfer member to the substrate degrades with time. This aging process of the coating does not seem to effect the adhesion of images which are already transferred to the substrate.

However, as is well known in the art, such substrate processing does not always lead to satisfactory results, especially in digital electrostatic printing.

SUMMARY OF THE INVENTION

One aspect of the present invention is a novel approach to the improvement of transferability and/or adhesion of images to substrates, especially plastic substrates.

10

15

20

25

30

In a broad view of the invention, a double coating is employed, with an underlayer having a high affinity for the substrate and an overlayer having a high affinity for the toner material. The two layers have a high affinity for each other.

In an exemplary embodiment of this aspect of the invention, the underlayer is a layer of an amine terminated polyamide such as Macromelt 6239 (Henkel) which was mentioned in the background of the invention. The upper layer is formed of material which has a high affinity for toner particles and which is also adheres well to the underlayer. As indicated above, an amine terminated polyamide has a high affinity for a wide rage of materials so that this seldom is a problem. Furthermore, the above mentioned deterioration of the properties of the amine terminated polyamide with time does not exist when it is coated with the overlayer.

Exemplary materials which are useful as overlayers include ethylene acrylic acid copolymer, polyvinyl pyridine and styrene butadiene copolymer. It is noted that these materials adhere rather poorly to untreated PET, BOPP, polycarbonate, polyethylene and vinyl. For some applications it is useful to reduce the degree of acidity of the ethylene acrylic acid copolymer, preferably by Saponification to a level of preferably between 8 and 18% acrylic acid comonomer weight percent, more preferably between 10 and 16%. Unmodified material typically has a acrylic acid comonomer weight percent of 20%.

A second aspect of the invention relates to substrates which are coated with ethylene acrylic acid copolymer, polyvinyl pyridine or styrene butadiene copolymer, and especially to substrates coated with ethylene acrylic acid copolymer with reduced acidity. Such coated substrates may, in some preferred embodiments of the invention, be plastic substrates such as PET or BOPP or, in other embodiments of the invention, may be paper.

A third aspect of the invention relates to the printing of images, preferably toner images and more preferably liquid toner images, on substrates of the invention or which are produced in accordance with the invention. This printing is preferably by transfer of the toner images to the substrate from an intermediate transfer member, to which it was transferred from an imaging surface. Preferred toners are based on one or more of ethylene vinyl acetate (EVA) copolymers, copolymers of ethylene and α , β - ethyleneically unsaturated acid selected from the group consisting of acrylic and methacrylic acids and ionomers such as are produced under the trade name of Surlyn, by Dupont.

There is therefore provided in accordance with a preferred embodiment of the invention, a substrate suitable for printing a toner image thereon, comprising:

10

15

20

25

30

a sheet of plastic;

an underlayer coating, on the sheet of plastic, comprising a first polymer material;

an overlayer coating, on the underlayer, comprising a second polymer material and having an outer surface to which a toner image can be fused and fixed.

Preferably, the sheet of plastic is PET. Alternatively, the sheet of plastic is BOPP. Alternatively, the sheet of plastic is polyethylene. Alternatively, the sheet of plastic is vinyl. Alternatively, the sheet of plastic is polycarbonate.

In a preferred embodiment of the invention, the overlayer comprises ethylene acrylic acid copolymer. Preferably, the ethylene acrylic acid copolymer has an acrylic acid comonomer percentage weight of less than 18%. Alternatively, the ethylene acrylic acid copolymer has an acrylic acid comonomer percentage weight of less than 16%.

Alternatively or additionally, the ethylene acrylic acid copolymer has an acrylic acid comonomer percentage weight of more than 8%. Alternatively, the ethylene acrylic acid copolymer has an acrylic acid comonomer percentage weight of more than 12%.

In a preferred embodiment of the invention, the overlayer comprises polyvinyl pyridine. Alternatively, the overlayer comprises styrene butadine copolymer.

In a preferred embodiment of the invention, the underlayer comprises amine terminated polyamide. Alternatively, the underlayer comprises a silane coupling agent. Alternatively, the underlayer comprises amino propyl teriethoxy silane.

In a preferred embodiment of the invention, the underlayer has a weight of between 0.1 and 1 grams per square meter. Alternatively or additionally, the underlayer has a weight of between about 0.3 and 0.5 grams per square meter.

In a preferred embodiment of the invention, the overlayer has a weight of between 0.1 and 10 grams per square meter. Alternatively or additionally, the overlayer has a weight of between 0.2 and 2 grams per square meter. Preferably, the overlayer has a weight of between about 0.25 and about 0.35 grams per square meter.

There is also provided in accordance with a preferred embodiment of the invention, a method of producing a coated substrate which a toner image can be adhered comprising:

coating a sheet of plastic with a first polymer material as an underlayer;

overcoating the underlayer with an second polymer material to form an overlayer coating on the underlayer, the overlayer having an outer surface to which a toner image can be adhered and fixed. Preferably, the coated substrate is a substrate as described above. There is

15

20

25

30

also provided in accordance with a preferred embodiment of the invention, a substrate produced according to the above described method.

There is also provided in accordance with a preferred embodiment of the invention, a substrate comprising a sheet chosen from the group consisting of PET, BOPP, polycarbonate, polyethylene and vinyl and an outer coating chosen from the group consisting of ethylene acrylic acid copolymer, polyvinyl pyridine and styrene butadine copolymer.

Preferably, the sheet is a PET sheet. Alternatively, the sheet is a BOPP sheet. Alternatively, the sheet is a polycarbonate sheet. Alternatively, the sheet is a polyethylene sheet. Alternatively, the sheet is a vinyl sheet.

Preferably, the coating comprises polyvinyl pyridine. Alternatively, the coating comprises styrene butadiene copolymer. Alternatively, the coating comprises ethylene acrylic acid copolymer. Preferably, the ethylene acrylic acid copolymer has an acrylic acid comonomer percentage weight of less than 18%.

There is also provided in accordance with a preferred embodiment of the invention, a substrate comprising a sheet and a coating of ethylene acrylic acid copolymer having an acrylic acid comonomer percentage weight of less than 18%.

Preferably, an ethylene acrylic acid copolymer, as described above, has an acrylic acid comonomer percentage weight of less than 16%. Alternatively, the ethylene acrylic acid copolymer has an acrylic acid comonomer percentage weight of more than 8%.

Preferably, the ethylene acrylic acid copolymer has an acrylic acid comonomer percentage weight of more than 12%.

Preferably, the coating, as described above, has a weight of between 0.1 and 0.4 grams per square meter. Preferably, the coating has a weight of between about 0.25 and about 0.35 grams per square meter.

There is also provided in accordance with a preferred embodiment of the invention, a printing method comprising:

providing a substrate, as described above; and

printing a toner image on the substrate.

Preferably, the toner image is a liquid toner image. Alternatively or additionally, printing comprises transferring the toner image to the substrate using heat and pressure.

Alternatively, printing comprises electrostatically transferring the toner image to the substrate.

In a preferred embodiment of the invention, the printing method comprises:

10

15

20

25

forming the image on an image forming surface;

transferring the image from the image forming surface to an intermediate transfer member; and

transferring the image from the intermediate transfer member to the substrate.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

A substrate according to a preferred embodiment of the present invention, on which a toner image is to be printed, comprises a plastic or other sheet coated with an underlayer having a high affinity for the substrate and an overlayer having a high affinity for the toner material. The two layers have a high affinity for each other.

One preferred, but non-limiting, method for producing such a substrate uses an underlayer of amine terminated polyamide and an overlayer of ethylene acrylic acid copolymer.

The underlayer

To 950 grams of 1-Propanal add 50 grams of Macromelt 6239 (Henkel), amine terminated polyamide, while stirring the mixture. Heat the material to between 40°C and 50°C until a homogeneous and clear 5% solids solution is obtained.

This material is applied to a substrate (for example an optionally corona treated BOPP substrate) by coating the substrate with the 5% solids solution and allowing the solution to dry, leaving a coating of preferably between about 0.1 and 0.3 grams of solid per square meter. This coating should be uniform. The coating may be applied by any one of the available methods of coating and, for example, using a rotogravure coating system. Alternatively a flexographic printing system can be used to apply the coating with the settings of the printer—controlling the thickness of the coating. However any other suitable coating process (double blade direct applicator, etc.) can be used. Other solution concentrations and other variations on the above described method can also be used.

While thinner and thicker coatings could be used, thinner coatings are not always effective and thicker coatings are more difficult to apply and expensive.

After application of the solution the coating is dried, preferably by an integral heater in the coating apparatus.

20

25

30

The overlayer

To 465 gm of deionized water add 200 g of isopropyl alcohol. This reaction is exothermic. After the mixture cools, add it to 335 g of a dispersion of MP 4990 (32-35%) as supplied by Michelman.

The dispersion is coated onto the underlayer by any convenient coating process, as for the underlayer, to give a coating of between approximately 0.3 - 0.5 grams per square meter although thinner coatings can be used.. If a double coating apparatus is available, the overlayer may be applied immediately over a dried underlayer.

After application of the overlayer solution the coating is dried, preferably by using the dryer integral in the coater. Other drying methods can also be used.

While the above formulation of overlayer material is suitable for printing on web fed material, it will adhere to surfaces with which it comes into contact, while hot, after printings, as, for example, an exit roller. To reduce the hot adhesivity, the degree of acidity of the ethylene acrylic acid copolymer, is reduced, preferably by Saponification to a level of preferably between 8 and 18% acrylic acid comonomer weight percent, more preferably between 10 and 16%. Unmodified material typically has a acrylic acid comonomer weight percent of 20%. This modified material can be used to directly coat paper and plastic substrates which do not require the adhesion promotion properties of the underlayer.

Other underlayer materials, for example, a silane coupling agent such as amino propyl triethoxy silane, may be used. The primary requirement for an underlayer is that it have high adhesion to the substrate and to the overlayer.

Other suitable overlayer materials include Polyvinyl pyridine (Molecular weight ...40,000 to 200,000) (Scientific Polymer Products). Additionally Styronal PK 8717 (BASF) (styrene butadiene copolymer) can be used as the overlayer. These material are preferably coated at a weight of approximately 0.5 grams per square meter.

Various bonding mechanisms can be utilized in various embodiments of the present invention. In the above example, the underlayer and overlayer are base and acid respectively. The toner described below is also acidic; however, the toner forms a strong chemical bond with the overlayer. Other materials, in accordance with preferred embodiment of the invention, utilize other types of bonding.

In general, a coating thickness (after drying) of between 0.1 to 10 micrometers is preferred. More preferably, the thickness is between 0.2 to 2 microns.

10

15

25

30

The coated substrates of the present invention are useful with a wide range of toner material which do not transfer easily to and/or adhere well to PET and BOPP. Preferred toners are based on one or more of ethylene vinyl acetate (EVA) copolymers, copolymers of ethylene and α , β - ethyleneically unsaturated acid selected from the group consisting of acrylic and methacrylic acids and ionomers such as are produced under the trade name of Surlyn, by Dupont.

One preferred method of forming a toner is the following:

1) Solubilization

1400 grams of Nucrel 925 (ethylene copolymer by Dupont) and 1400 grams of Isopar L (Exxon) are thoroughly mixed in an oil heated Ross double planetary mixer at at least 24 RPM for 1.5 hours, with the oil temperature at 130°C. 1200 grams of preheated Isopar L is added and mixing is continued for an additional hour. The mixture is cooled to 45°C, while stirring is continued, over a period of several hours, to form a viscous material.

2) Milling and Grinding

762 grams of the result of the solubilizing step are ground in a 1S attritor (Union Process Inc. Acron, Ohio), charged with 3/16" carbon steel balls, at 250 RPM, together with 66.7 grams of Mogul L carbon black (Cabot), 6.7 grams of BT583D (blue pigment produced by Cookson), 5 grams of aluminum tri stearate and an additional 1459.6 grams of Isopar L, for eight hours at 30°C.

20 3) Continuation of Grinding

34.5 grams of ACumist A-12 is added and grinding is continued for an additional 4-12 hours. The resulting particles are fibrous particles having a measured diameter in the range of 1-3 micrometers.

The resulting material is diluted with additional Isopar L and Marcol 82 to give a working developer in which the dry solids portion is about 1.7% and in which the overall ratio of Isopar L to Marcol is between about 50:1 and 500:1, normally about 100:1.

Charge director as described in US patent application 07/915,291 (utilizing Lecithin BBP and ICIG3300B) and in WO 94/02887, in an amount equal to 40 mg/gm of solids, is added to charge the tone particles. Other charge directors and additional additives, as known in the art may also be used.

In a preferred embodiment of the invention the substrate is printed using an intermediate transfer member to transfer images to the substrate and to fuse and fix them

PDN

thereto. Preferred apparatus for such printing are the E-Print 1000 and the E-Print Omnius printers marketed by Indigo NV.

The present invention has been described utilizing preferred embodiments thereof. It should be understood that the details of the coating processes and exact formulations of the coatings and liquid toners are meant to be exemplary in nature and not to limit the claims. In particular the invention also includes materials which are listed in the summary and claims for the substrate, the underlayer, the overlayer and the toner, as well as different combinations of materials chosen from the four groups of materials.

CLAIMS

- A substrate suitable for printing a toner image thereon, comprising:

 a sheet of plastic;
 an underlayer coating, on the sheet of plastic, comprising a first polymer material;
 an overlayer coating, on the underlayer, comprising a second polymer material and
 having an outer surface to which a toner image can be fused and fixed.
 - 2. A substrate according to claim 1 wherein the sheet of plastic is PET.
- 10 3. A substrate according to claim 1 wherein the sheet of plastic is BOPP.
 - 4. A substrate according to claim 1 wherein the sheet of plastic is polyethylene.
 - 5. A substrate according to claim 1 wherein the sheet of plastic is vinyl.
 - 6. A substrate according to claim 1 wherein the sheet of plastic is polycarbonate.
 - 7. A substrate according to any of the preceding claims wherein the overlayer comprises ethylene acrylic acid copolymer.
 - A substrate according to claim 7 wherein the ethylene acrylic acid copolymer has an acrylic acid comonomer percentage weight of less than 18%.
 - A substrate according to claim 7 wherein the ethylene acrylic acid copolymer has an
 acrylic acid comonomer percentage weight of less than 16%.
 - 10. A substrate according to any of claims 7-9 wherein the ethylene acrylic acid copolymer has an acrylic acid comonomer percentage weight of more than 8%.
 - 30 11. A substrate according to any of claims 7-9 wherein the ethylene acrylic acid copolymer has an acrylic acid comonomer percentage weight of more than 12%.

- 12. A substrate according to any of claims 1-6 wherein the overlayer comprises polyvinyl pyridine.
- 13. A substrate according to any of claims 1-6 wherein the overlayer comprises styrene butadine copolymer.
 - 14. A substrate according to any of the preceding claims wherein the underlayer comprises amine terminated polyamide.
- 10 15. A substrate according to any of claims 1-13 wherein the underlayer comprises a silane coupling agent.
 - 16. A substrate according to any of claims 1-13 wherein the underlayer comprises amino propyl teriethoxy silane.
- 17. A substrate according to any of the preceding claims wherein the underlayer has a weight of between 0.1 and 1 grams per square meter.
- 18. A substrate according to any of the preceding claims wherein the underlayer has a weight of between about 0.3 and 0.5 grams per square meter.
 - 19. A substrate according to any of the preceding claims wherein the overlayer has a weight of between 0.1 and 10 grams per square meter.
- 25 20. A substrate according to any of the preceding claims wherein the overlayer has a weight of between 0.2 and 2 grams per square meter.
 - 21. A substrate according to claim 20 wherein the overlayer has a weight of between about 0.25 and about 0.35 grams per square meter.
- 22. A method of producing a coated substrate which a toner image can be adhered comprising:

coating a sheet of plastic with a first polymer material as an underlayer;

overcoating the underlayer with an second polymer material to form an overlayer coating on the underlayer, the overlayer having an outer surface to which a toner image can be adhered and fixed.

- 5
- 23. A method according to claim 22 wherein the coated substrate is a substrate according to any of claims 1-21.
- 24. A substrate produced according to the method of claim 22.
- 10
- 25. A substrate comprising a sheet chosen from the group consisting of PET, BOPP, polycarbonate, polyethylene and vinyl and an outer coating chosen from the group consisting of ethylene acrylic acid copolymer, polyvinyl pyridine and styrene butadine copolymer.
- 15 26. A substrate according to claim 25 wherein the sheet is a PET sheet.
 - 27. A substrate according to claim 25 wherein the sheet is a BOPP sheet.
 - 28. A substrate according to claim 25 wherein the sheet is a polycarbonate sheet.
- 20
- 29. A substrate according to claim 25 wherein the sheet is a polyethylene sheet.
- A substrate according to claim 25, wherein the sheet is a vinyl sheet.
- 25 31. A substrate according to any of claims 25-30 wherein the coating comprises polyvinyl pyridine.
 - 32. A substrate according to any of claims 25-30 wherein the coating comprises styrene butadiene copolymer.
- 30
- 33. A substrate according to any of claims 25-30 wherein the coating comprises ethylene acrylic acid copolymer.

- 34. A substrate according to claim 33 wherein the ethylene acrylic acid copolymer has an acrylic acid comonomer percentage weight of less than 18%.
- 5 35. A substrate comprising a sheet and a coating of ethylene acrylic acid copolymer having an acrylic acid comonomer percentage weight of less than 18%.
 - 36. A substrate according to any of claims 33-35 wherein the ethylene acrylic acid copolymer has an acrylic acid comonomer percentage weight of less than 16%.
- 37. A substrate according to any of claims 33-36 wherein the ethylene acrylic acid copolymer has an acrylic acid comonomer percentage weight of more than 8%.
 - 38. A substrate according to any of claims 33-37 wherein the ethylene acrylic acid copolymer has an acrylic acid comonomer percentage weight of more than 12%.
 - 39. A substrate according to any of claims 25-38 wherein the coating has a weight of between 0.1 and 0.4 grams per square meter.
 - 20 40. A substrate according to claim 39 wherein the coating has a weight of between about 0.25 and about 0.35 grams per square meter.
 - 41. A printing method comprising:

 providing a substrate according to any of claims 1-21 or 24-40; and
 printing a toner image on the substrate.
 - 42. A printing method according to claim 41 wherein the toner image is a liquid toner image.
 - 30 43. A printing method according to claim 41 or claim 42 wherein printing comprises transferring the toner image to the substrate using heat and pressure.

10

- 44. A printing method according to claim 41 or 42 wherein printing comprises electrostatically transferring the toner image to the substrate.
- 45. A printing method according to any of claims 41-44 and comprising:

 forming the image on an image forming surface;

 transferring the image from the image forming surface to an intermediate transfer
 member; and

transferring the image from the intermediate transfer member to the substrate.



ABSTRACT

A substrate suitable for printing a toner image thereon, comprising:

a sheet of plastic;

an underlayer coating, on the sheet of plastic, comprising a first polymer material; and an overlayer coating, on the underlayer, comprising a second polymer material and having an outer surface to which a toner image can be adhered and fixed.